

Technical Information

ABS Virgin Standard type

Overview

ABS Virgin Standard type is an excellent general purpose extrusion / thermoforming resin with outstanding processability. The mass (continuous process) ABS technology of the supplier ensures an ABS resin that combines excellent processability with a stable light base colour that is ideal for self-colouring. The ABS Virgin Standard type has an ultra low particulate content, which results in a superb surface finish that will enable our customers to produce parts with excellent aesthetics at a lower total cost.

Applications:

- Transportation
- Sanitary ware
- Signage
- Furnishings
- Protective covers
- Marine
- Recreational vehicles

Physical	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Density	1.05	g/cm ³	1.05	g/cm ³	ISO 1183/B
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	4.7	g/10min	4.7	g/10min	ISO 1133
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	0.409	in ³ /10min	6.70	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow	0.0040 to 0.0070	in/in	0.40 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Tensile Modulus					
0.126 in (3.20 mm), Injection Molded	312000	psi	2150	MPa	ISO 527-2
Tensile Stress					
Yield, 0.126 in (3.20 mm), Injection Molded	624 0	psi	43.0	MPa	ISO 527-2/50
Tensile Strain					
Yield, 0.126 in (3.20 mm), Injection Molded	2.7	%	2.7	%	ISO 527-2/50
Flexural Modulus					
0.126 in (3.20 mm), Injection Molded	305000	psi	2100	MPa	ISO 178 ^{1,2}
Flexural Strength					
0.126 in (3.20 mm), Injection Molded	10200	psi	70.0	MPa	ISO 178 ^{1,2}
Impact	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Charpy Notched Impact Strength					
-22°F (-30°C), Injection Molded	6.2	ft•lb/in ²	13	kJ/m ²	ISO 179/1eA ISO
-22°F (-30°C), Injection Molded	3.8	ft•lb/in ²	8.0	kJ/m ²	179/1eA
73°F (23°C), Injection Molded	8.6	ft•lb/in ²	18	kJ/m ²	179/2C ISO
73°F (23°C), Injection Molded	6.2	ft•lb/in ²	13	kJ/m ²	ISO 179/2C
Notched Izod Impact Strength					
-22°F (-30°C), Injection Molded	5.2	ft•lb/in ²	11	kJ/m ²	ISO 180/A
73°F (23°C), Injection Molded	9.0	ft•lb/in ²	19	kJ/m ²	
Thermal	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Heat Deflection Temperature					
264 psi (1.8 MPa), Annealed	214	°F	101	°C	ISO 75-2/A
Vicat Softening Temperature	216	°F	102	°C	ISO 306/B50
Flammability	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Burning Rate (0.0787 in (2.00 mm))	2.0	in/min	50	mm/min	ISO 3795 ³
Flame Rating - UL					UL 94 ³
0.0591 in (1.50 mm)		HB		HB	
0.118 in (3.00 mm)		HB		HB	

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ 0.079 in/min (2.0 mm/min)

² 3-points

³ This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.



Universal Polythex Kunststoffe GmbH Friedrich-Ebert-Straße 15 52531 Übach-Palenberg

Product Stewardship

The supplier has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with the supplier products EI from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

The supplier strongly encourages its customers to review both their manufacturing processes and their applications of the supplier products from the standpoint of human health and environmental quality to ensure that the supplier products are not used in ways for which they are not intended or tested. The supplier personnel are available to answer your questions and to provide reasonable technical support. The supplier product literature, including safety data sheets, should be consulted prior to use of the supplier products. Current safety data sheets are available from the supplier.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: The supplier will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:
long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
use as a critical component in medical devices that support or sustain human life; or use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

The supplier requests that customers considering use of the supplier products in medical applications notify the supplier so that appropriate assessments may be conducted. The supplier does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the supplier product is safe, lawful, and technically suitable for the intended use. THE SUPPLIER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY THE SUPPLIER PRODUCT FOR USE IN MEDICAL APPLICATIONS.

Disclaimer

NOTICE: No freedom from infringement of any patent owned by the supplier or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. The supplier assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Responsible Care®

NOTICE: If products are described as "experimental" or "developmental": (1)

product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for the supplier to change specifications and/or discontinue production; and (4) although the supplier may from time to time provide samples of such products, the supplier is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

Our top priority is to provide the highest quality products and services, and to focus on the American Chemistry Council's Responsible Care® initiative and safety in all of our facilities.